


Aluminium Anode A-388-K

gross weight: 38,80 kg
net weight: 35,20 kg



Technical specification AlZnIn - alloy type A2 according to EN12496:2013 :

Alloying elements:		Impurities:	
Zn [%]:	3,0 - 5,5	Fe [%]:	max 0,09
In [%]:	0,016 - 0,040	Cu [%]:	max 0,005
Al -	balance	Si [%]:	max 0,10

Electrochemical efficiency min: 2500 Ah/kg
according to DNV RP B401 test appendix B

Note:

- All weights and dimensions are nominal.
- Dimensions in mm

 MAKROMOR CATHODIC PROTECTION	MAKROMOR SP. Z O.O. Ul. Gołębia 15 81-185 Gdynia, POLAND Phone: +48 58 661-57-99 Fax: +48 58 661-01-89 e-mail: biuro@makromor.pl website: www.makromor.pl	Scale:
		Insert type: S235JR
Type: ALUMINIUM ANODE A-388-K		Alloy: AlZnIn
Product code: A388/A-388-K/186/100/720/900/0		Alternative type:
Drawer: Łukasz Stabek		Drawing No.: A388K/0
Date: 16-02-2016	Approved: Grzegorz Pryłowski	Date: 16-02-2016
Copyright MAKROMOR SP. Z O.O. All rights reserved.		